



## Deflection and Sightline Reference Guide

This document has been developed to assist with process of selecting glass to withstand loads, minimize center of glass deflection and identify the appropriate sightline.

The ability of glass to withstand a load is calculated utilizing ASTM E1300 Standard Practice for Determining Load Resistance of Glass in Buildings.

The glass unit size, ply thicknesses and heat treatment impact the strength and center of glass deflection.

The ability of the insulating unit seal to support the insulating unit and exterior glass ply in a structurally glazed application is calculated utilizing ASTM C1249 Standard Guide for Secondary Seal for Sealed Insulating Glass Units for Structural Sealant Glazing Applications.

### Using this Reference Guide

- ① Locate the page with your intended glass unit make-up and heat treatment. See index below.
- ② Locate the applicable load along the left side.
- ③ Within the applicable load section, follow the glass width until it meets the height of your unit.
- ④ Review the center of glass deflection and sightline .

### Index

Insulating		Insulating Laminated		Laminated Insulating	
1" HS	pg 2	1-5/16" HS	pg 4	1-5/16" HS	pg 6
1" FT	pg 3	1-5/16" FT	pg 5	1-5/16" FT	pg 7

### Definitions

**Conventionally Glazed:** A framing system captures the glazing in a channel so the framing system surrounds the glass and is visible around the full perimeter of each glass unit.

**Deflection (center of glass):** The amount the center of a glass lite bends, perpendicular to the plane of the glass surface, under an applied load. When deflection is >1", increase the glass ply thickness or decrease the size to achieve a center of glass ≤1".

**Fully Tempered Glass (FT):** Glass that has been heat-treated to have either a minimum surface compression of 10000 psi or an edge compression not less than 9700 psi in accordance with the requirements of ASTM C1048 kind FT or meet the requirements of ANSI Z97.1 or CPSC 16 CFR 1201 safety glazing standards. Tempered glass is 4-5 times stronger than annealed glass and when broken breaks into small relatively harmless pieces.

**Heat Strengthened (HS):** Glass that has been heat-treated to have a surface compression between 3500 and 7500 psi and meets the requirements for ASTM C1048, kind HS. It is 2-3 times stronger than annealed glass. HS is not a safety glazing material and will not meet the requirements of ANSI Z97.1 or CPSC 16 CFR 1201.

**Sightline:** Edge dimension of insulating glass covered by spacer. All insulating units have a sightline. Insulating glass used in a conventionally glazed system typically utilizes a 1/2" sightline. When used in a structurally glazed system, the insulating glass sightline is calculated based on the unit size and design loads in order to appropriately support the insulating unit and exterior glass ply.

**Structurally Glazed:** The use of a silicone sealant on one or more sides of the insulating unit for the structural transfer of loads from the glass to its perimeter support system and retention of the glass in the opening. When structurally glazed, the framing system is typically not visible on the exterior facade along the structurally glazed sides.

**Two sided structurally glazed:** Glass structurally adhered to metal back-up mullion and two sides captured in pocket

**Four sided structurally glazed:** Glass with four sides structurally adhered to metal back-up mullion.

### Deflection and Sightline Reference Guide

1" Insulating Unit																											
Constructed with two plies of 1/4" heat strengthened (HS) glass																											
Wind Load	Width (Base)	Height																									
		24"		36"		48"		60"		72"		84"		96"		108"		120"		132"		144"		156"		168"	
		Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline
60 psf	24"	0.03"	1/2"	0.05"	1/2"	0.07"	1/2"	0.09"	1/2"	0.09"	1/2"	0.09"	1/2"	0.09"	1/2"	0.09"	1/2"	0.09"	1/2"	0.09"	1/2"	0.10"	1/2"	0.10"	1/2"	0.10"	1/2"
	36"	0.05"	1/2"	0.15"	5/8"	0.21"	5/8"	0.27"	5/8"	0.32"	5/8"	0.36"	5/8"	0.39"	5/8"	0.41"	5/8"	0.42"	5/8"	0.44"	5/8"	0.44"	5/8"	0.44"	5/8"	0.45"	5/8"
	48"	0.07"	1/2"	0.21"	5/8"	0.33"	5/8"	0.43"	5/8"	0.53"	5/8"	0.62"	5/8"	0.71"	5/8"	0.79"	5/8"	0.86"	5/8"	0.93"	5/8"	1.00"	5/8"	1.00"	5/8"	1.06"	5/8"
	60"	0.09"	1/2"	0.27"	5/8"	0.43"	5/8"	0.56"	3/4"	0.69"	N/A	0.82"	N/A	0.94"	N/A	1.06"	N/A	1.19"	N/A	1.31"	N/A	1.44"	N/A	1.44"	N/A	FT req.	FT req.
	72"	0.09"	1/2"	0.32"	5/8"	0.53"	5/8"	0.69"	3/4"	0.81"	N/A	0.96"	N/A	1.11"	N/A	1.26"	N/A	1.41"	N/A	1.57"	N/A	1.73"	N/A	1.73"	N/A	FT req.	FT req.
	84"	0.09"	1/2"	0.36"	5/8"	0.62"	5/8"	0.82"	3/4"	0.96"	N/A	1.07"	N/A	1.24"	N/A	1.40"	N/A	1.57"	N/A	1.75"	N/A	FT req.	FT req.	FT req.	FT req.	FT req.	FT req.
50 psf	24"	0.00"	1/2"	0.04"	1/2"	0.06"	1/2"	0.07"	1/2"	0.08"	1/2"	0.08"	1/2"	0.08"	1/2"	0.07"	1/2"	0.07"	1/2"	0.07"	1/2"	0.08"	1/2"	0.08"	1/2"	0.08"	1/2"
	36"	0.04"	1/2"	0.13"	5/8"	0.18"	5/8"	0.23"	5/8"	0.28"	5/8"	0.31"	5/8"	0.33"	5/8"	0.35"	5/8"	0.36"	5/8"	0.37"	5/8"	0.38"	5/8"	0.38"	5/8"	0.38"	5/8"
	48"	0.06"	1/2"	0.18"	5/8"	0.30"	5/8"	0.39"	5/8"	0.48"	5/8"	0.56"	5/8"	0.63"	5/8"	0.70"	5/8"	0.76"	5/8"	0.82"	5/8"	0.87"	5/8"	0.87"	5/8"	0.92"	5/8"
	60"	0.07"	1/2"	0.23"	5/8"	0.39"	5/8"	0.50"	3/4"	0.62"	N/A	0.74"	N/A	0.85"	N/A	0.97"	N/A	1.07"	N/A	1.18"	N/A	1.29"	N/A	1.29"	N/A	1.41"	N/A
	72"	0.08"	1/2"	0.28"	5/8"	0.48"	5/8"	0.62"	3/4"	0.74"	N/A	0.88"	N/A	1.02"	N/A	1.16"	N/A	1.29"	N/A	1.44"	N/A	1.58"	N/A	1.58"	N/A	1.74"	N/A
	84"	0.08"	1/2"	0.31"	5/8"	0.56"	5/8"	0.74"	3/4"	0.88"	N/A	0.99"	N/A	1.14"	N/A	1.30"	N/A	1.45"	N/A	1.61"	N/A	1.78"	N/A	1.78"	N/A	1.95"	N/A
40 psf	24"	0.00"	1/2"	0.01"	1/2"	0.04"	1/2"	0.06"	1/2"	0.06"	1/2"	0.06"	1/2"	0.06"	1/2"	0.06"	1/2"	0.06"	1/2"	0.06"	1/2"	0.07"	1/2"	0.07"	1/2"	0.07"	1/2"
	36"	0.01"	1/2"	0.03"	1/2"	0.15"	1/2"	0.20"	1/2"	0.23"	1/2"	0.26"	1/2"	0.28"	1/2"	0.29"	1/2"	0.30"	1/2"	0.30"	1/2"	0.30"	1/2"	0.30"	1/2"	0.31"	1/2"
	48"	0.04"	1/2"	0.15"	1/2"	0.25"	5/8"	0.34"	5/8"	0.41"	5/8"	0.48"	5/8"	0.55"	5/8"	0.60"	5/8"	0.65"	5/8"	0.70"	5/8"	0.74"	5/8"	0.74"	5/8"	0.78"	5/8"
	60"	0.06"	1/2"	0.20"	1/2"	0.34"	5/8"	0.44"	5/8"	0.55"	5/8"	0.66"	5/8"	0.76"	5/8"	0.85"	5/8"	0.95"	5/8"	1.04"	5/8"	1.13"	5/8"	1.13"	5/8"	1.22"	5/8"
	72"	0.06"	1/2"	0.23"	1/2"	0.41"	5/8"	0.55"	5/8"	0.66"	5/8"	0.79"	5/8"	0.91"	5/8"	1.04"	5/8"	1.16"	5/8"	1.30"	5/8"	1.41"	5/8"	1.41"	5/8"	1.54"	5/8"
	84"	0.06"	1/2"	0.26"	1/2"	0.48"	5/8"	0.66"	5/8"	0.79"	5/8"	0.89"	N/A	1.03"	N/A	1.17"	N/A	1.32"	N/A	1.46"	N/A	1.61"	N/A	1.61"	N/A	1.76"	N/A
30 psf	24"	0.01"	1/2"	0.02"	1/2"	0.03"	1/2"	0.04"	1/2"	0.04"	1/2"	0.05"	1/2"	0.04"	1/2"	0.04"	1/2"	0.04"	1/2"	0.04"	1/2"	0.05"	1/2"	0.05"	1/2"	0.05"	1/2"
	36"	0.02"	1/2"	0.08"	1/2"	0.12"	1/2"	0.15"	1/2"	0.18"	1/2"	0.20"	1/2"	0.22"	1/2"	0.22"	1/2"	0.23"	1/2"	0.23"	1/2"	0.23"	1/2"	0.23"	1/2"	0.23"	1/2"
	48"	0.03"	1/2"	0.12"	1/2"	0.21"	1/2"	0.27"	1/2"	0.34"	1/2"	0.40"	1/2"	0.45"	1/2"	0.49"	1/2"	0.53"	1/2"	0.56"	1/2"	0.59"	1/2"	0.59"	1/2"	0.62"	1/2"
	60"	0.04"	1/2"	0.15"	1/2"	0.27"	1/2"	0.38"	5/8"	0.47"	5/8"	0.56"	5/8"	0.64"	5/8"	0.72"	5/8"	0.80"	5/8"	0.87"	5/8"	0.94"	5/8"	0.94"	5/8"	1.01"	5/8"
	72"	0.04"	1/2"	0.18"	1/2"	0.34"	1/2"	0.47"	5/8"	0.57"	5/8"	0.68"	5/8"	0.79"	5/8"	0.90"	5/8"	1.00"	5/8"	1.11"	5/8"	1.21"	5/8"	1.21"	5/8"	1.32"	5/8"
	84"	0.05"	1/2"	0.20"	1/2"	0.40"	1/2"	0.56"	5/8"	0.68"	5/8"	0.78"	5/8"	0.90"	5/8"	1.03"	5/8"	1.15"	5/8"	1.28"	5/8"	1.40"	5/8"	1.40"	5/8"	1.53"	5/8"
96"	0.04"	1/2"	0.22"	1/2"	0.45"	1/2"	0.64"	5/8"	0.79"	5/8"	0.90"	5/8"	1.00"	5/8"	1.14"	5/8"	1.27"	5/8"	1.41"	5/8"	1.55"	5/8"	1.55"	5/8"	1.69"	5/8"	

Values are for vertically installed glass. For sloped glazing calculations, contact Viracon. Deflection is center of glass based on ASTM E1300 and is calculated using Window Glass Design (WGD5). Sightline is for structurally glazed units based on ASTM C1249. When conventionally glazed, the minimum sightline is 1/2".

\*\* Load resistance calculations for 1/4" thick glass are limited to a long dimension of 200 inches by WGD5.

\*\*\* These glass dimensions fall outside the range of the 1/4" non-factored load chart.

N/A = The required sightline for structural glazing is Not Available from Velocity.

## Deflection and Sightline Reference Guide

1" Insulating Unit																															
<i>Constructed with two plies of 1/4" fully tempered (FT) glass</i>																															
Wind Load	Width (Base)	Height																													
		24"		36"		48"		60"		72"		84"		96"		108"		120"		132"		144"		156"		168"					
		Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline				
<b>60 psf</b>	24"	0.03"	1/2"	0.05"	1/2"	0.07"	1/2"	0.09"	1/2"	0.09"	1/2"	0.09"	1/2"	0.09"	1/2"	0.09"	1/2"	0.09"	1/2"	0.09"	1/2"	0.10"	1/2"	0.10"	1/2"	0.10"	1/2"				
	36"	0.05"	1/2"	0.15"	5/8"	0.21"	5/8"	0.27"	5/8"	0.32"	5/8"	0.36"	5/8"	0.39"	5/8"	0.41"	5/8"	0.42"	5/8"	0.44"	5/8"	0.44"	5/8"	0.44"	5/8"	0.45"	5/8"	0.46"	5/8"		
	48"	0.07"	1/2"	0.21"	5/8"	0.33"	5/8"	0.43"	5/8"	0.53"	5/8"	0.62"	5/8"	0.71"	5/8"	0.79"	5/8"	0.86"	5/8"	0.93"	5/8"	1.00"	5/8"	1.00"	5/8"	1.06"	5/8"	1.13"	5/8"		
	60"	0.09"	1/2"	0.27"	5/8"	0.43"	5/8"	0.56"	N/A	0.69"	N/A	0.82"	N/A	0.94"	N/A	1.06"	N/A	1.19"	N/A	1.31"	N/A	1.44"	N/A	1.44"	N/A	1.57"	N/A	1.71"	N/A		
	72"	0.09"	1/2"	0.32"	5/8"	0.53"	5/8"	0.69"	N/A	0.81"	N/A	0.96"	N/A	1.11"	N/A	1.26"	N/A	1.41"	N/A	1.57"	N/A	1.73"	N/A	1.73"	N/A	1.91"	N/A	1.91"	N/A	2.09"	N/A
	96"	0.09"	1/2"	0.36"	5/8"	0.62"	5/8"	0.82"	N/A	0.96"	N/A	1.07"	N/A	1.24"	N/A	1.40"	N/A	1.57"	N/A	1.75"	N/A	1.93"	N/A	1.93"	N/A	2.12"	N/A	2.12"	N/A	2.33"	N/A
<b>50 psf</b>	24"	0.00"	1/2"	0.04"	1/2"	0.06"	1/2"	0.07"	1/2"	0.08"	1/2"	0.08"	1/2"	0.08"	1/2"	0.07"	1/2"	0.07"	1/2"	0.08"	1/2"	0.08"	1/2"	0.08"	1/2"	0.08"	1/2"	0.08"	1/2"		
	36"	0.04"	1/2"	0.13"	5/8"	0.18"	5/8"	0.23"	5/8"	0.28"	5/8"	0.31"	5/8"	0.33"	5/8"	0.35"	5/8"	0.36"	5/8"	0.37"	5/8"	0.38"	5/8"	0.38"	5/8"	0.38"	5/8"	0.38"	5/8"	0.38"	5/8"
	48"	0.06"	1/2"	0.18"	5/8"	0.30"	5/8"	0.39"	5/8"	0.48"	5/8"	0.56"	5/8"	0.63"	5/8"	0.70"	5/8"	0.76"	5/8"	0.82"	5/8"	0.87"	5/8"	0.87"	5/8"	0.92"	5/8"	0.98"	5/8"	0.98"	5/8"
	60"	0.07"	1/2"	0.23"	5/8"	0.39"	5/8"	0.50"	N/A	0.62"	N/A	0.74"	N/A	0.85"	N/A	0.97"	N/A	1.07"	N/A	1.18"	N/A	1.29"	N/A	1.29"	N/A	1.41"	N/A	1.52"	N/A	1.52"	N/A
	72"	0.08"	1/2"	0.28"	5/8"	0.48"	5/8"	0.62"	N/A	0.74"	N/A	0.88"	N/A	1.02"	N/A	1.16"	N/A	1.29"	N/A	1.44"	N/A	1.58"	N/A	1.74"	N/A	1.74"	N/A	1.90"	N/A	1.90"	N/A
	96"	0.08"	1/2"	0.31"	5/8"	0.56"	5/8"	0.74"	N/A	0.88"	N/A	0.99"	N/A	1.14"	N/A	1.30"	N/A	1.45"	N/A	1.61"	N/A	1.78"	N/A	1.95"	N/A	1.95"	N/A	2.14"	N/A	2.14"	N/A
<b>40 psf</b>	24"	0.00"	1/2"	0.01"	1/2"	0.04"	1/2"	0.06"	1/2"	0.06"	1/2"	0.06"	1/2"	0.06"	1/2"	0.06"	1/2"	0.06"	1/2"	0.06"	1/2"	0.06"	1/2"	0.07"	1/2"	0.07"	1/2"	0.07"	1/2"		
	36"	0.01"	1/2"	0.03"	1/2"	0.15"	1/2"	0.20"	1/2"	0.23"	1/2"	0.26"	1/2"	0.28"	1/2"	0.29"	1/2"	0.30"	1/2"	0.30"	1/2"	0.30"	1/2"	0.30"	1/2"	0.31"	1/2"	0.31"	1/2"		
	48"	0.04"	1/2"	0.15"	1/2"	0.25"	5/8"	0.34"	5/8"	0.41"	5/8"	0.48"	5/8"	0.55"	5/8"	0.60"	5/8"	0.65"	5/8"	0.70"	5/8"	0.74"	5/8"	0.74"	5/8"	0.78"	5/8"	0.81"	5/8"		
	60"	0.06"	1/2"	0.20"	1/2"	0.34"	5/8"	0.44"	5/8"	0.55"	5/8"	0.66"	5/8"	0.76"	5/8"	0.85"	5/8"	0.95"	5/8"	1.04"	5/8"	1.13"	5/8"	1.13"	5/8"	1.22"	5/8"	1.32"	5/8"		
	72"	0.06"	1/2"	0.23"	1/2"	0.41"	5/8"	0.55"	5/8"	0.66"	5/8"	0.79"	5/8"	0.91"	5/8"	1.04"	5/8"	1.16"	5/8"	1.30"	5/8"	1.41"	5/8"	1.41"	5/8"	1.54"	5/8"	1.68"	5/8"		
	96"	0.06"	1/2"	0.26"	1/2"	0.48"	5/8"	0.66"	5/8"	0.79"	5/8"	0.89"	N/A	1.03"	N/A	1.17"	N/A	1.32"	N/A	1.46"	N/A	1.61"	N/A	1.61"	N/A	1.76"	N/A	1.92"	N/A		
<b>30 psf</b>	24"	0.01"	1/2"	0.02"	1/2"	0.03"	1/2"	0.04"	1/2"	0.04"	1/2"	0.05"	1/2"	0.04"	1/2"	0.04"	1/2"	0.04"	1/2"	0.05"	1/2"	0.05"	1/2"	0.05"	1/2"	0.05"	1/2"	0.05"	1/2"		
	36"	0.02"	1/2"	0.08"	1/2"	0.12"	1/2"	0.15"	1/2"	0.18"	1/2"	0.20"	1/2"	0.22"	1/2"	0.22"	1/2"	0.23"	1/2"	0.23"	1/2"	0.23"	1/2"	0.23"	1/2"	0.23"	1/2"	0.23"	1/2"		
	48"	0.03"	1/2"	0.12"	1/2"	0.21"	1/2"	0.27"	1/2"	0.34"	1/2"	0.40"	1/2"	0.45"	1/2"	0.49"	1/2"	0.53"	1/2"	0.56"	1/2"	0.59"	1/2"	0.59"	1/2"	0.62"	1/2"	0.64"	1/2"		
	60"	0.04"	1/2"	0.15"	1/2"	0.27"	1/2"	0.38"	5/8"	0.47"	5/8"	0.56"	5/8"	0.64"	5/8"	0.72"	5/8"	0.80"	5/8"	0.87"	5/8"	0.94"	5/8"	1.01"	5/8"	1.08"	5/8"	1.08"	5/8"		
	72"	0.04"	1/2"	0.18"	1/2"	0.34"	1/2"	0.47"	5/8"	0.57"	5/8"	0.68"	5/8"	0.79"	5/8"	0.90"	5/8"	1.00"	5/8"	1.11"	5/8"	1.21"	5/8"	1.21"	5/8"	1.32"	5/8"	1.43"	5/8"		
	84"	0.05"	1/2"	0.20"	1/2"	0.40"	1/2"	0.56"	5/8"	0.68"	5/8"	0.78"	5/8"	0.90"	5/8"	1.03"	5/8"	1.15"	5/8"	1.28"	5/8"	1.40"	5/8"	1.40"	5/8"	1.53"	5/8"	1.67"	5/8"		
96"	0.04"	1/2"	0.22"	1/2"	0.45"	1/2"	0.64"	5/8"	0.79"	5/8"	0.90"	5/8"	1.00"	5/8"	1.14"	5/8"	1.27"	5/8"	1.41"	5/8"	1.55"	5/8"	1.69"	5/8"	1.69"	5/8"	1.84"	5/8"			

Values are for vertically installed glass. For sloped glazing calculations, contact Viracon. Deflection is center of glass based on ASTM E1300 and is calculated using Window Glass Design (WGD5). Sightline is for structurally glazed units based on ASTM C1249. When conventionally glazed, the minimum sightline is 1/2".

\*\* Load resistance calculations for 1/4" thick glass are limited to a long dimension of 200 inches by WGD5.

\*\*\* These glass dimensions fall outside the range of the 1/4" non-factored load chart.

N/A = The required sightline for structural glazing is Not Available from Velocity.

### Deflection and Sightline Reference Guide

1-5/16" Insulating Laminated Unit																															
Constructed with a 1/4" outboard and two plies of 1/4" laminated on the inboard, all plies heat strengthened (HS) glass																															
Wind Load	Width (Base)	Height																													
		24"		36"		48"		60"		72"		84"		96"		108"		120"		132"		144"		156"		168"					
		Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline				
60 psf	24"	0.02"	1/2"	0.04"	1/2"	0.07"	1/2"	0.07"	1/2"	0.06"	1/2"	0.06"	1/2"	0.04"	1/2"	0.04"	1/2"	0.04"	1/2"	0.05"	1/2"	0.06"	1/2"	0.06"	1/2"	0.06"	1/2"	0.07"	1/2"		
	36"	0.04"	1/2"	0.10"	1/2"	0.17"	1/2"	0.20"	1/2"	0.23"	1/2"	0.23"	1/2"	0.23"	1/2"	0.21"	1/2"	0.21"	1/2"	0.20"	1/2"	0.18"	1/2"	0.19"	1/2"	0.19"	1/2"	0.19"	1/2"		
	48"	0.07"	1/2"	0.17"	1/2"	0.24"	1/2"	0.29"	1/2"	0.34"	1/2"	0.39"	1/2"	0.44"	1/2"	0.45"	1/2"	0.47"	1/2"	0.49"	1/2"	0.50"	1/2"	0.51"	1/2"	0.51"	1/2"	0.51"	1/2"		
	60"	0.07"	1/2"	0.20"	1/2"	0.29"	1/2"	0.38"	1/2"	0.45"	1/2"	0.51"	1/2"	0.58"	1/2"	0.65"	1/2"	0.73"	1/2"	0.77"	1/2"	0.81"	1/2"	0.86"	1/2"	0.86"	1/2"	0.91"	1/2"		
	72"	0.06"	1/2"	0.23"	1/2"	0.34"	1/2"	0.45"	1/2"	0.54"	1/2"	0.64"	1/2"	0.72"	1/2"	0.81"	1/2"	0.90"	1/2"	1.00"	1/2"	1.09"	1/2"	1.17"	1/2"	FT req.					
	84"	0.06"	1/2"	0.23"	1/2"	0.39"	1/2"	0.51"	1/2"	0.64"	1/2"	0.75"	1/2"	0.86"	1/2"	0.96"	1/2"	1.07"	1/2"	1.18"	1/2"	1.30"	1/2"	FT req.		FT req.					
	96"	0.04"	1/2"	0.23"	1/2"	0.44"	1/2"	0.58"	1/2"	0.72"	1/2"	0.86"	1/2"	0.99"	1/2"	1.11"	1/2"	1.24"	1/2"	1.37"	1/2"	1.50"	1/2"	FT req.		FT req.					
50 psf	24"	0.02"	1/2"	0.03"	1/2"	0.06"	1/2"	0.06"	1/2"	0.05"	1/2"	0.05"	1/2"	0.04"	1/2"	0.04"	1/2"	0.03"	1/2"	0.04"	1/2"	0.05"	1/2"	0.05"	1/2"	0.05"	1/2"	0.05"	1/2"	0.06"	1/2"
	36"	0.03"	1/2"	0.09"	1/2"	0.14"	1/2"	0.18"	1/2"	0.21"	1/2"	0.21"	1/2"	0.20"	1/2"	0.19"	1/2"	0.18"	1/2"	0.17"	1/2"	0.16"	1/2"	0.16"	1/2"	0.16"	1/2"	0.16"	1/2"		
	48"	0.06"	1/2"	0.14"	1/2"	0.22"	1/2"	0.26"	1/2"	0.31"	1/2"	0.36"	1/2"	0.40"	1/2"	0.41"	1/2"	0.42"	1/2"	0.43"	1/2"	0.44"	1/2"	0.44"	1/2"	0.44"	1/2"	0.45"	1/2"		
	60"	0.06"	1/2"	0.18"	1/2"	0.26"	1/2"	0.34"	1/2"	0.41"	1/2"	0.46"	1/2"	0.52"	1/2"	0.59"	1/2"	0.65"	1/2"	0.69"	1/2"	0.73"	1/2"	0.76"	1/2"	0.80"	1/2"	0.80"	1/2"		
	72"	0.05"	1/2"	0.21"	1/2"	0.31"	1/2"	0.41"	1/2"	0.49"	1/2"	0.57"	1/2"	0.66"	1/2"	0.73"	1/2"	0.82"	1/2"	0.90"	1/2"	0.99"	1/2"	1.05"	1/2"	1.12"	1/2"	1.12"	1/2"		
	84"	0.04"	1/2"	0.21"	1/2"	0.36"	1/2"	0.46"	1/2"	0.57"	1/2"	0.68"	1/2"	0.78"	1/2"	0.88"	1/2"	0.97"	1/2"	1.07"	1/2"	1.18"	1/2"	1.28"	1/2"	1.39"	1/2"	1.39"	1/2"		
	96"	0.04"	1/2"	0.20"	1/2"	0.40"	1/2"	0.52"	1/2"	0.66"	1/2"	0.78"	1/2"	0.90"	1/2"	1.01"	1/2"	1.13"	1/2"	1.24"	1/2"	1.36"	1/2"	1.48"	1/2"	***		1/2"			
40 psf	24"	0.01"	1/2"	0.03"	1/2"	0.04"	1/2"	0.05"	1/2"	0.04"	1/2"	0.04"	1/2"	0.03"	1/2"	0.03"	1/2"	0.03"	1/2"	0.03"	1/2"	0.04"	1/2"	0.04"	1/2"	0.04"	1/2"	0.04"	1/2"	0.05"	1/2"
	36"	0.03"	1/2"	0.07"	1/2"	0.11"	1/2"	0.16"	1/2"	0.18"	1/2"	0.18"	1/2"	0.17"	1/2"	0.16"	1/2"	0.15"	1/2"	0.15"	1/2"	0.13"	1/2"	0.13"	1/2"	0.13"	1/2"	0.13"	1/2"		
	48"	0.04"	1/2"	0.11"	1/2"	0.19"	1/2"	0.24"	1/2"	0.28"	1/2"	0.31"	1/2"	0.35"	1/2"	0.36"	1/2"	0.36"	1/2"	0.36"	1/2"	0.37"	1/2"	0.37"	1/2"	0.37"	1/2"	0.37"	1/2"		
	60"	0.05"	1/2"	0.16"	1/2"	0.24"	1/2"	0.31"	1/2"	0.36"	1/2"	0.42"	1/2"	0.46"	1/2"	0.52"	1/2"	0.58"	1/2"	0.61"	1/2"	0.63"	1/2"	0.66"	1/2"	0.66"	1/2"	0.69"	1/2"		
	72"	0.04"	1/2"	0.18"	1/2"	0.28"	1/2"	0.36"	1/2"	0.45"	1/2"	0.51"	1/2"	0.58"	1/2"	0.65"	1/2"	0.72"	1/2"	0.80"	1/2"	0.87"	1/2"	0.92"	1/2"	0.92"	1/2"	0.97"	1/2"		
	84"	0.04"	1/2"	0.18"	1/2"	0.31"	1/2"	0.42"	1/2"	0.51"	1/2"	0.61"	1/2"	0.69"	1/2"	0.78"	1/2"	0.86"	1/2"	0.95"	1/2"	1.04"	1/2"	1.13"	1/2"	1.23"	1/2"	1.23"	1/2"		
	96"	0.03"	1/2"	0.17"	1/2"	0.35"	1/2"	0.46"	1/2"	0.58"	1/2"	0.69"	1/2"	0.80"	1/2"	0.90"	1/2"	1.00"	1/2"	1.10"	1/2"	1.21"	1/2"	1.32"	1/2"	***		1/2"			
30 psf	24"	0.01"	1/2"	0.02"	1/2"	0.03"	1/2"	0.04"	1/2"	0.03"	1/2"	0.03"	1/2"	0.02"	1/2"	0.02"	1/2"	0.02"	1/2"	0.02"	1/2"	0.03"	1/2"	0.03"	1/2"	0.03"	1/2"	0.03"	1/2"	0.04"	1/2"
	36"	0.02"	1/2"	0.05"	1/2"	0.09"	1/2"	0.13"	1/2"	0.16"	1/2"	0.15"	1/2"	0.14"	1/2"	0.13"	1/2"	0.12"	1/2"	0.11"	1/2"	0.10"	1/2"	0.10"	1/2"	0.10"	1/2"	0.10"	1/2"		
	48"	0.03"	1/2"	0.09"	1/2"	0.16"	1/2"	0.20"	1/2"	0.24"	1/2"	0.27"	1/2"	0.30"	1/2"	0.31"	1/2"	0.31"	1/2"	0.30"	1/2"	0.30"	1/2"	0.30"	1/2"	0.30"	1/2"	0.30"	1/2"		
	60"	0.04"	1/2"	0.13"	1/2"	0.20"	1/2"	0.27"	1/2"	0.31"	1/2"	0.36"	1/2"	0.40"	1/2"	0.44"	1/2"	0.49"	1/2"	0.51"	1/2"	0.53"	1/2"	0.54"	1/2"	0.54"	1/2"	0.56"	1/2"		
	72"	0.03"	1/2"	0.16"	1/2"	0.24"	1/2"	0.31"	1/2"	0.39"	1/2"	0.44"	1/2"	0.49"	1/2"	0.55"	1/2"	0.62"	1/2"	0.68"	1/2"	0.74"	1/2"	0.78"	1/2"	0.78"	1/2"	0.82"	1/2"		
	84"	0.03"	1/2"	0.15"	1/2"	0.27"	1/2"	0.36"	1/2"	0.44"	1/2"	0.52"	1/2"	0.59"	1/2"	0.67"	1/2"	0.74"	1/2"	0.82"	1/2"	0.89"	1/2"	0.97"	1/2"	0.97"	1/2"	1.05"	1/2"		
	96"	0.02"	1/2"	0.14"	1/2"	0.30"	1/2"	0.40"	1/2"	0.49"	1/2"	0.59"	1/2"	0.69"	1/2"	0.78"	1/2"	0.86"	1/2"	0.95"	1/2"	1.04"	1/2"	1.13"	1/2"	***		1/2"			

Values are for vertically installed glass. For sloped glazing calculations, contact Viracon. Deflection is center of glass based on ASTM E1300 and is calculated using Window Glass Design (WGD5). Sightline is for structurally glazed units based on ASTM C1249. When conventionally glazed, the minimum sightline is 1/2".

\*\* Load resistance calculations for 1/4" thick glass are limited to a long dimension of 200 inches by WGD5.

\*\*\* These glass dimensions fall outside the range of the 1/4" non-factored load chart.

N/A = The required sightline for structural glazing is Not Available from Velocity.

### Deflection and Sightline Reference Guide

1-5/16" Insulating Laminated Unit																											
Constructed with a 1/4" outboard and two plies of 1/4" laminated on the inboard, all plies fully tempered (FT) glass																											
Wind Load	Width (Base)	Height																									
		24"		36"		48"		60"		72"		84"		96"		108"		120"		132"		144"		156"		168"	
		Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline
60 psf	24"	0.02"	1/2"	0.04"	1/2"	0.07"	1/2"	0.07"	1/2"	0.06"	1/2"	0.06"	1/2"	0.04"	1/2"	0.04"	1/2"	0.04"	1/2"	0.05"	1/2"	0.06"	1/2"	0.06"	1/2"	0.07"	1/2"
	36"	0.04"	1/2"	0.10"	1/2"	0.17"	1/2"	0.20"	1/2"	0.23"	1/2"	0.23"	1/2"	0.23"	1/2"	0.21"	1/2"	0.21"	1/2"	0.20"	1/2"	0.18"	1/2"	0.19"	1/2"	0.19"	1/2"
	48"	0.07"	1/2"	0.17"	1/2"	0.24"	1/2"	0.29"	1/2"	0.34"	1/2"	0.39"	1/2"	0.44"	1/2"	0.45"	1/2"	0.47"	1/2"	0.49"	1/2"	0.50"	1/2"	0.51"	1/2"	0.51"	1/2"
	60"	0.07"	1/2"	0.20"	1/2"	0.29"	1/2"	0.38"	1/2"	0.45"	1/2"	0.51"	1/2"	0.58"	1/2"	0.65"	1/2"	0.73"	1/2"	0.77"	1/2"	0.81"	1/2"	0.86"	1/2"	0.91"	1/2"
	72"	0.06"	1/2"	0.23"	1/2"	0.34"	1/2"	0.45"	1/2"	0.54"	1/2"	0.64"	1/2"	0.72"	1/2"	0.81"	1/2"	0.90"	1/2"	1.00"	1/2"	1.09"	1/2"	1.17"	1/2"	1.25"	1/2"
	84"	0.06"	1/2"	0.23"	1/2"	0.39"	1/2"	0.51"	1/2"	0.64"	1/2"	0.75"	1/2"	0.86"	1/2"	0.96"	1/2"	1.07"	1/2"	1.18"	1/2"	1.30"	1/2"	1.42"	1/2"	1.54"	1/2"
	96"	0.04"	1/2"	0.23"	1/2"	0.44"	1/2"	0.58"	1/2"	0.72"	1/2"	0.86"	1/2"	0.99"	1/2"	1.11"	1/2"	1.24"	1/2"	1.37"	1/2"	1.50"	1/2"	1.64"	1/2"	***	1/2"
50 psf	24"	0.02"	1/2"	0.03"	1/2"	0.06"	1/2"	0.06"	1/2"	0.05"	1/2"	0.05"	1/2"	0.04"	1/2"	0.04"	1/2"	0.03"	1/2"	0.04"	1/2"	0.05"	1/2"	0.05"	1/2"	0.06"	1/2"
	36"	0.03"	1/2"	0.09"	1/2"	0.14"	1/2"	0.18"	1/2"	0.21"	1/2"	0.21"	1/2"	0.20"	1/2"	0.19"	1/2"	0.18"	1/2"	0.17"	1/2"	0.16"	1/2"	0.16"	1/2"	0.16"	1/2"
	48"	0.06"	1/2"	0.14"	1/2"	0.22"	1/2"	0.26"	1/2"	0.31"	1/2"	0.36"	1/2"	0.40"	1/2"	0.41"	1/2"	0.42"	1/2"	0.43"	1/2"	0.44"	1/2"	0.44"	1/2"	0.45"	1/2"
	60"	0.06"	1/2"	0.18"	1/2"	0.26"	1/2"	0.34"	1/2"	0.41"	1/2"	0.46"	1/2"	0.52"	1/2"	0.59"	1/2"	0.65"	1/2"	0.69"	1/2"	0.73"	1/2"	0.76"	1/2"	0.80"	1/2"
	72"	0.05"	1/2"	0.21"	1/2"	0.31"	1/2"	0.41"	1/2"	0.49"	1/2"	0.57"	1/2"	0.66"	1/2"	0.73"	1/2"	0.82"	1/2"	0.90"	1/2"	0.99"	1/2"	1.05"	1/2"	1.12"	1/2"
	84"	0.04"	1/2"	0.21"	1/2"	0.36"	1/2"	0.46"	1/2"	0.57"	1/2"	0.68"	1/2"	0.78"	1/2"	0.88"	1/2"	0.97"	1/2"	1.07"	1/2"	1.18"	1/2"	1.28"	1/2"	1.39"	1/2"
	96"	0.04"	1/2"	0.20"	1/2"	0.40"	1/2"	0.52"	1/2"	0.66"	1/2"	0.78"	1/2"	0.90"	1/2"	1.01"	1/2"	1.13"	1/2"	1.24"	1/2"	1.36"	1/2"	1.48"	1/2"	***	1/2"
40 psf	24"	0.01"	1/2"	0.03"	1/2"	0.04"	1/2"	0.05"	1/2"	0.04"	1/2"	0.04"	1/2"	0.03"	1/2"	0.03"	1/2"	0.03"	1/2"	0.03"	1/2"	0.04"	1/2"	0.04"	1/2"	0.05"	1/2"
	36"	0.03"	1/2"	0.07"	1/2"	0.11"	1/2"	0.16"	1/2"	0.18"	1/2"	0.18"	1/2"	0.17"	1/2"	0.16"	1/2"	0.15"	1/2"	0.15"	1/2"	0.13"	1/2"	0.13"	1/2"	0.13"	1/2"
	48"	0.04"	1/2"	0.11"	1/2"	0.19"	1/2"	0.24"	1/2"	0.28"	1/2"	0.31"	1/2"	0.35"	1/2"	0.36"	1/2"	0.36"	1/2"	0.36"	1/2"	0.37"	1/2"	0.37"	1/2"	0.37"	1/2"
	60"	0.05"	1/2"	0.16"	1/2"	0.24"	1/2"	0.31"	1/2"	0.38"	1/2"	0.42"	1/2"	0.46"	1/2"	0.52"	1/2"	0.58"	1/2"	0.61"	1/2"	0.63"	1/2"	0.66"	1/2"	0.69"	1/2"
	72"	0.04"	1/2"	0.18"	1/2"	0.28"	1/2"	0.36"	1/2"	0.45"	1/2"	0.51"	1/2"	0.58"	1/2"	0.65"	1/2"	0.72"	1/2"	0.80"	1/2"	0.87"	1/2"	0.92"	1/2"	0.97"	1/2"
	84"	0.04"	1/2"	0.18"	1/2"	0.31"	1/2"	0.42"	1/2"	0.51"	1/2"	0.61"	1/2"	0.69"	1/2"	0.78"	1/2"	0.86"	1/2"	0.95"	1/2"	1.04"	1/2"	1.13"	1/2"	1.23"	1/2"
	96"	0.03"	1/2"	0.17"	1/2"	0.35"	1/2"	0.46"	1/2"	0.58"	1/2"	0.69"	1/2"	0.80"	1/2"	0.90"	1/2"	1.00"	1/2"	1.10"	1/2"	1.21"	1/2"	1.32"	1/2"	***	1/2"
30 psf	24"	0.01"	1/2"	0.02"	1/2"	0.03"	1/2"	0.04"	1/2"	0.03"	1/2"	0.03"	1/2"	0.02"	1/2"	0.02"	1/2"	0.02"	1/2"	0.02"	1/2"	0.03"	1/2"	0.03"	1/2"	0.04"	1/2"
	36"	0.02"	1/2"	0.05"	1/2"	0.09"	1/2"	0.13"	1/2"	0.16"	1/2"	0.15"	1/2"	0.14"	1/2"	0.13"	1/2"	0.12"	1/2"	0.11"	1/2"	0.10"	1/2"	0.10"	1/2"	0.10"	1/2"
	48"	0.03"	1/2"	0.09"	1/2"	0.16"	1/2"	0.20"	1/2"	0.24"	1/2"	0.27"	1/2"	0.30"	1/2"	0.31"	1/2"	0.31"	1/2"	0.30"	1/2"	0.30"	1/2"	0.30"	1/2"	0.30"	1/2"
	60"	0.04"	1/2"	0.13"	1/2"	0.20"	1/2"	0.27"	1/2"	0.31"	1/2"	0.36"	1/2"	0.40"	1/2"	0.44"	1/2"	0.49"	1/2"	0.51"	1/2"	0.53"	1/2"	0.54"	1/2"	0.56"	1/2"
	72"	0.03"	1/2"	0.16"	1/2"	0.24"	1/2"	0.31"	1/2"	0.39"	1/2"	0.44"	1/2"	0.49"	1/2"	0.55"	1/2"	0.62"	1/2"	0.68"	1/2"	0.74"	1/2"	0.78"	1/2"	0.82"	1/2"
	84"	0.03"	1/2"	0.15"	1/2"	0.27"	1/2"	0.36"	1/2"	0.44"	1/2"	0.52"	1/2"	0.59"	1/2"	0.67"	1/2"	0.74"	1/2"	0.82"	1/2"	0.89"	1/2"	0.97"	1/2"	1.05"	1/2"
	96"	0.02"	1/2"	0.14"	1/2"	0.30"	1/2"	0.40"	1/2"	0.49"	1/2"	0.59"	1/2"	0.69"	1/2"	0.78"	1/2"	0.86"	1/2"	0.95"	1/2"	1.04"	1/2"	1.13"	1/2"	***	1/2"

Values are for vertically installed glass. For sloped glazing calculations, contact Viracon. Deflection is center of glass based on ASTM E1300 and is calculated using Window Glass Design (WGD5). Sightline is for structurally glazed units based on ASTM C1249. When conventionally glazed, the minimum sightline is 1/2".

\*\* Load resistance calculations for 1/4" thick glass are limited to a long dimension of 200 inches by WGD5.

\*\*\* These glass dimensions fall outside the range of the 1/4" non-factored load chart.

N/A = The required sightline for structural glazing is Not Available from Velocity.

### Deflection and Sightline Reference Guide

1-5/16" Laminated Insulating Unit																											
Constructed with two plies of 1/4" laminated on the outboard a 1/4" inboard, all plies heat strengthened (HS) glass																											
Wind Load	Width (Base)	Height																									
		24"		36"		48"		60"		72"		84"		96"		108"		120"		132"		144"		156"		168"	
		Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline
60 psf	24"	0.02"	5/8"	0.04"	5/8"	0.07"	5/8"	0.07"	5/8"	0.06"	5/8"	0.06"	5/8"	0.04"	5/8"	0.04"	5/8"	0.04"	5/8"	0.05"	5/8"	0.06"	5/8"	0.06"	5/8"	0.07"	5/8"
	36"	0.04"	5/8"	0.10"	N/A	0.17"	N/A	0.20"	N/A	0.23"	N/A	0.23"	N/A	0.23"	N/A	0.21"	N/A	0.21"	N/A	0.20"	N/A	0.18"	N/A	0.19"	N/A	0.19"	N/A
	48"	0.07"	5/8"	0.17"	N/A	0.24"	N/A	0.29"	N/A	0.34"	N/A	0.39"	N/A	0.44"	N/A	0.45"	N/A	0.47"	N/A	0.49"	N/A	0.50"	N/A	0.51"	N/A	0.51"	N/A
	60"	0.07"	5/8"	0.20"	N/A	0.29"	N/A	0.38"	N/A	0.45"	N/A	0.51"	N/A	0.58"	N/A	0.65"	N/A	0.73"	N/A	0.77"	N/A	0.81"	N/A	0.86"	N/A	0.91"	N/A
	72"	0.06"	5/8"	0.23"	N/A	0.34"	N/A	0.45"	N/A	0.54"	N/A	0.64"	N/A	0.72"	N/A	0.81"	N/A	0.90"	N/A	1.00"	N/A	1.09"	N/A	1.17"	N/A	FT req.	
	84"	0.06"	5/8"	0.23"	N/A	0.39"	N/A	0.51"	N/A	0.64"	N/A	0.75"	N/A	0.86"	N/A	0.96"	N/A	1.07"	N/A	1.18"	N/A	1.30"	N/A	FT req.		FT req.	
	96"	0.04"	5/8"	0.23"	N/A	0.44"	N/A	0.58"	N/A	0.72"	N/A	0.86"	N/A	0.99"	N/A	1.11"	N/A	1.24"	N/A	1.37"	N/A	1.50"	N/A	FT req.		FT req.	
50 psf	24"	0.02"	5/8"	0.03"	5/8"	0.06"	5/8"	0.06"	5/8"	0.05"	5/8"	0.05"	5/8"	0.04"	5/8"	0.04"	5/8"	0.03"	5/8"	0.04"	5/8"	0.05"	5/8"	0.05"	5/8"	0.06"	5/8"
	36"	0.03"	5/8"	0.09"	N/A	0.14"	N/A	0.18"	N/A	0.21"	N/A	0.21"	N/A	0.20"	N/A	0.19"	N/A	0.18"	N/A	0.17"	N/A	0.16"	N/A	0.16"	N/A	0.16"	N/A
	48"	0.06"	5/8"	0.14"	N/A	0.22"	N/A	0.26"	N/A	0.31"	N/A	0.36"	N/A	0.40"	N/A	0.41"	N/A	0.42"	N/A	0.43"	N/A	0.44"	N/A	0.44"	N/A	0.44"	N/A
	60"	0.06"	5/8"	0.18"	N/A	0.26"	N/A	0.34"	N/A	0.41"	N/A	0.46"	N/A	0.52"	N/A	0.59"	N/A	0.65"	N/A	0.69"	N/A	0.73"	N/A	0.76"	N/A	0.80"	N/A
	72"	0.05"	5/8"	0.21"	N/A	0.31"	N/A	0.41"	N/A	0.49"	N/A	0.57"	N/A	0.66"	N/A	0.73"	N/A	0.82"	N/A	0.90"	N/A	0.99"	N/A	1.05"	N/A	1.12"	N/A
	84"	0.04"	5/8"	0.21"	N/A	0.36"	N/A	0.46"	N/A	0.57"	N/A	0.68"	N/A	0.78"	N/A	0.88"	N/A	0.97"	N/A	1.07"	N/A	1.18"	N/A	1.28"	N/A	1.39"	N/A
	96"	0.04"	5/8"	0.20"	N/A	0.40"	N/A	0.52"	N/A	0.66"	N/A	0.78"	N/A	0.90"	N/A	1.01"	N/A	1.13"	N/A	1.24"	N/A	1.36"	N/A	1.48"	N/A	***	N/A
40 psf	24"	0.01"	5/8"	0.03"	5/8"	0.04"	5/8"	0.05"	5/8"	0.04"	5/8"	0.04"	5/8"	0.03"	5/8"	0.03"	5/8"	0.03"	5/8"	0.03"	5/8"	0.04"	5/8"	0.04"	5/8"	0.05"	5/8"
	36"	0.03"	5/8"	0.07"	5/8"	0.11"	5/8"	0.16"	5/8"	0.18"	5/8"	0.18"	5/8"	0.17"	5/8"	0.16"	5/8"	0.15"	5/8"	0.15"	5/8"	0.13"	5/8"	0.13"	5/8"	0.13"	5/8"
	48"	0.04"	5/8"	0.11"	5/8"	0.19"	N/A	0.24"	N/A	0.28"	N/A	0.31"	N/A	0.35"	N/A	0.36"	N/A	0.36"	N/A	0.36"	N/A	0.37"	N/A	0.37"	N/A	0.37"	N/A
	60"	0.05"	5/8"	0.16"	5/8"	0.24"	N/A	0.31"	N/A	0.36"	N/A	0.42"	N/A	0.46"	N/A	0.52"	N/A	0.58"	N/A	0.61"	N/A	0.63"	N/A	0.66"	N/A	0.69"	N/A
	72"	0.04"	5/8"	0.18"	5/8"	0.28"	N/A	0.36"	N/A	0.45"	N/A	0.51"	N/A	0.58"	N/A	0.65"	N/A	0.72"	N/A	0.80"	N/A	0.87"	N/A	0.92"	N/A	0.97"	N/A
	84"	0.04"	5/8"	0.18"	5/8"	0.31"	N/A	0.42"	N/A	0.51"	N/A	0.61"	N/A	0.69"	N/A	0.78"	N/A	0.86"	N/A	0.95"	N/A	1.04"	N/A	1.13"	N/A	1.23"	N/A
	96"	0.03"	5/8"	0.17"	5/8"	0.35"	N/A	0.46"	N/A	0.58"	N/A	0.69"	N/A	0.80"	N/A	0.90"	N/A	1.00"	N/A	1.10"	N/A	1.21"	N/A	1.32"	N/A	***	N/A
30 psf	24"	0.01"	1/2"	0.02"	1/2"	0.03"	1/2"	0.04"	1/2"	0.03"	1/2"	0.03"	1/2"	0.02"	1/2"	0.02"	1/2"	0.02"	1/2"	0.02"	1/2"	0.03"	1/2"	0.03"	1/2"	0.04"	1/2"
	36"	0.02"	1/2"	0.05"	5/8"	0.09"	5/8"	0.13"	5/8"	0.16"	5/8"	0.15"	5/8"	0.14"	5/8"	0.13"	5/8"	0.12"	5/8"	0.11"	5/8"	0.10"	5/8"	0.10"	5/8"	0.10"	5/8"
	48"	0.03"	1/2"	0.09"	5/8"	0.16"	5/8"	0.20"	5/8"	0.24"	5/8"	0.27"	5/8"	0.30"	5/8"	0.31"	5/8"	0.31"	5/8"	0.30"	5/8"	0.30"	5/8"	0.30"	5/8"	0.30"	5/8"
	60"	0.04"	1/2"	0.13"	5/8"	0.20"	5/8"	0.27"	N/A	0.31"	N/A	0.36"	N/A	0.40"	N/A	0.44"	N/A	0.49"	N/A	0.51"	N/A	0.53"	N/A	0.54"	N/A	0.56"	N/A
	72"	0.03"	1/2"	0.16"	5/8"	0.24"	5/8"	0.31"	N/A	0.39"	N/A	0.44"	N/A	0.49"	N/A	0.55"	N/A	0.62"	N/A	0.68"	N/A	0.74"	N/A	0.78"	N/A	0.82"	N/A
	84"	0.03"	1/2"	0.15"	5/8"	0.27"	5/8"	0.36"	N/A	0.44"	N/A	0.52"	N/A	0.59"	N/A	0.67"	N/A	0.74"	N/A	0.82"	N/A	0.89"	N/A	0.97"	N/A	1.05"	N/A
	96"	0.02"	1/2"	0.14"	5/8"	0.30"	5/8"	0.40"	N/A	0.49"	N/A	0.59"	N/A	0.69"	N/A	0.78"	N/A	0.86"	N/A	0.95"	N/A	1.04"	N/A	1.13"	N/A	***	N/A

Values are for vertically installed glass. For sloped glazing calculations, contact Viracon. Deflection is center of glass based on ASTM E1300 and is calculated using Window Glass Design (WGD5). Sightline is for structurally glazed units based on ASTM C1249. When conventionally glazed, the minimum sightline is 1/2".

\*\* Load resistance calculations for 1/4" thick glass are limited to a long dimension of 200 inches by WGD5.

\*\*\* These glass dimensions fall outside the range of the 1/4" non-factored load chart.

N/A = The required sightline for structural glazing is Not Available from Velocity.

### Deflection and Sightline Reference Guide

1-5/16" Laminated Insulating Unit																											
Constructed with two plies of 1/4" laminated on the outboard a 1/4" inboard, all plies fully tempered (FT) glass																											
Wind Load	Width (Base)	Height																									
		24"		36"		48"		60"		72"		84"		96"		108"		120"		132"		144"		156"		168"	
		Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline	Deflection	Sightline
60 psf	24"	0.02"	5/8"	0.04"	5/8"	0.07"	5/8"	0.07"	5/8"	0.06"	5/8"	0.06"	5/8"	0.04"	5/8"	0.04"	5/8"	0.04"	5/8"	0.05"	5/8"	0.06"	5/8"	0.06"	5/8"	0.07"	5/8"
	36"	0.04"	5/8"	0.10"	N/A	0.17"	N/A	0.20"	N/A	0.23"	N/A	0.23"	N/A	0.23"	N/A	0.21"	N/A	0.21"	N/A	0.20"	N/A	0.18"	N/A	0.19"	N/A	0.19"	N/A
	48"	0.07"	5/8"	0.17"	N/A	0.24"	N/A	0.29"	N/A	0.34"	N/A	0.39"	N/A	0.44"	N/A	0.45"	N/A	0.47"	N/A	0.49"	N/A	0.50"	N/A	0.51"	N/A	0.51"	N/A
	60"	0.07"	5/8"	0.20"	N/A	0.29"	N/A	0.38"	N/A	0.45"	N/A	0.51"	N/A	0.58"	N/A	0.65"	N/A	0.73"	N/A	0.77"	N/A	0.81"	N/A	0.86"	N/A	0.91"	N/A
	72"	0.06"	5/8"	0.23"	N/A	0.34"	N/A	0.45"	N/A	0.54"	N/A	0.64"	N/A	0.72"	N/A	0.81"	N/A	0.90"	N/A	1.00"	N/A	1.09"	N/A	1.17"	N/A	1.25"	N/A
	84"	0.06"	5/8"	0.23"	N/A	0.39"	N/A	0.51"	N/A	0.64"	N/A	0.75"	N/A	0.86"	N/A	0.96"	N/A	1.07"	N/A	1.18"	N/A	1.30"	N/A	1.42"	N/A	1.54"	N/A
50 psf	24"	0.02"	5/8"	0.03"	5/8"	0.06"	5/8"	0.06"	5/8"	0.05"	5/8"	0.05"	5/8"	0.04"	5/8"	0.04"	5/8"	0.03"	5/8"	0.04"	5/8"	0.05"	5/8"	0.05"	5/8"	0.06"	5/8"
	36"	0.03"	5/8"	0.09"	N/A	0.14"	N/A	0.18"	N/A	0.21"	N/A	0.21"	N/A	0.20"	N/A	0.19"	N/A	0.18"	N/A	0.17"	N/A	0.16"	N/A	0.16"	N/A	0.16"	N/A
	48"	0.06"	5/8"	0.14"	N/A	0.22"	N/A	0.26"	N/A	0.31"	N/A	0.36"	N/A	0.40"	N/A	0.41"	N/A	0.42"	N/A	0.43"	N/A	0.44"	N/A	0.44"	N/A	0.45"	N/A
	60"	0.06"	5/8"	0.18"	N/A	0.26"	N/A	0.34"	N/A	0.41"	N/A	0.46"	N/A	0.52"	N/A	0.59"	N/A	0.65"	N/A	0.69"	N/A	0.73"	N/A	0.76"	N/A	0.80"	N/A
	72"	0.05"	5/8"	0.21"	N/A	0.31"	N/A	0.41"	N/A	0.49"	N/A	0.57"	N/A	0.66"	N/A	0.73"	N/A	0.82"	N/A	0.90"	N/A	0.99"	N/A	1.05"	N/A	1.12"	N/A
	84"	0.04"	5/8"	0.21"	N/A	0.36"	N/A	0.46"	N/A	0.57"	N/A	0.68"	N/A	0.78"	N/A	0.88"	N/A	0.97"	N/A	1.07"	N/A	1.18"	N/A	1.28"	N/A	1.39"	N/A
40 psf	24"	0.01"	5/8"	0.03"	5/8"	0.04"	5/8"	0.05"	5/8"	0.04"	5/8"	0.04"	5/8"	0.03"	5/8"	0.03"	5/8"	0.03"	5/8"	0.03"	5/8"	0.04"	5/8"	0.04"	5/8"	0.05"	5/8"
	36"	0.03"	5/8"	0.07"	5/8"	0.11"	5/8"	0.16"	5/8"	0.18"	5/8"	0.18"	5/8"	0.17"	5/8"	0.16"	5/8"	0.15"	5/8"	0.15"	5/8"	0.13"	5/8"	0.13"	5/8"	0.13"	5/8"
	48"	0.04"	5/8"	0.11"	5/8"	0.19"	N/A	0.24"	N/A	0.28"	N/A	0.31"	N/A	0.35"	N/A	0.36"	N/A	0.36"	N/A	0.36"	N/A	0.37"	N/A	0.37"	N/A	0.37"	N/A
	60"	0.05"	5/8"	0.16"	5/8"	0.24"	N/A	0.31"	N/A	0.36"	N/A	0.42"	N/A	0.46"	N/A	0.52"	N/A	0.58"	N/A	0.61"	N/A	0.63"	N/A	0.66"	N/A	0.69"	N/A
	72"	0.04"	5/8"	0.18"	5/8"	0.28"	N/A	0.36"	N/A	0.45"	N/A	0.51"	N/A	0.58"	N/A	0.65"	N/A	0.72"	N/A	0.80"	N/A	0.87"	N/A	0.92"	N/A	0.97"	N/A
	84"	0.04"	5/8"	0.18"	5/8"	0.31"	N/A	0.42"	N/A	0.51"	N/A	0.61"	N/A	0.69"	N/A	0.78"	N/A	0.86"	N/A	0.95"	N/A	1.04"	N/A	1.13"	N/A	1.23"	N/A
30 psf	24"	0.01"	1/2"	0.02"	1/2"	0.03"	1/2"	0.04"	1/2"	0.03"	1/2"	0.03"	1/2"	0.02"	1/2"	0.02"	1/2"	0.02"	1/2"	0.02"	1/2"	0.03"	1/2"	0.03"	1/2"	0.04"	1/2"
	36"	0.02"	1/2"	0.05"	5/8"	0.09"	5/8"	0.13"	5/8"	0.16"	5/8"	0.15"	5/8"	0.14"	5/8"	0.13"	5/8"	0.12"	5/8"	0.11"	5/8"	0.10"	5/8"	0.10"	5/8"	0.10"	5/8"
	48"	0.03"	1/2"	0.09"	5/8"	0.16"	5/8"	0.20"	5/8"	0.24"	5/8"	0.27"	5/8"	0.30"	5/8"	0.31"	5/8"	0.31"	5/8"	0.30"	5/8"	0.30"	5/8"	0.30"	5/8"	0.30"	5/8"
	60"	0.04"	1/2"	0.13"	5/8"	0.20"	5/8"	0.27"	N/A	0.31"	N/A	0.36"	N/A	0.40"	N/A	0.44"	N/A	0.49"	N/A	0.51"	N/A	0.53"	N/A	0.54"	N/A	0.56"	N/A
	72"	0.03"	1/2"	0.16"	5/8"	0.24"	5/8"	0.31"	N/A	0.39"	N/A	0.44"	N/A	0.49"	N/A	0.55"	N/A	0.62"	N/A	0.68"	N/A	0.74"	N/A	0.78"	N/A	0.82"	N/A
	84"	0.03"	1/2"	0.15"	5/8"	0.27"	5/8"	0.36"	N/A	0.44"	N/A	0.52"	N/A	0.59"	N/A	0.67"	N/A	0.74"	N/A	0.82"	N/A	0.89"	N/A	0.97"	N/A	1.05"	N/A
96"	0.02"	1/2"	0.14"	5/8"	0.30"	5/8"	0.40"	N/A	0.49"	N/A	0.59"	N/A	0.69"	N/A	0.78"	N/A	0.86"	N/A	0.95"	N/A	1.04"	N/A	1.13"	N/A	***	N/A	

Values are for vertically installed glass. For sloped glazing calculations, contact Viracon. Deflection is center of glass based on ASTM E1300 and is calculated using Window Glass Design (WGD5). Sightline is for structurally glazed units based on ASTM C1249. When conventionally glazed, the minimum sightline is 1/2".

\*\* Load resistance calculations for 1/4" thick glass are limited to a long dimension of 200 inches by WGD5.

\*\*\* These glass dimensions fall outside the range of the 1/4" non-factored load chart.

N/A = The required sightline for structural glazing is Not Available from Velocity.